10/574053

± ¹ IAP5 Rec'd PCT/PTO 2 9 MAR 2006

AMENDMENT

To: Examiner of the Patent Office

5   1.   Identification of the International Application
        PCT/JP2004/014790

       2.   Applicant
          Name: NIPPON STEEL CORPORATION
10   Address: 6-3, Otemachi 2-chome, Chiyoda-ku, Tokyo
                  100-8071 Japan
         Country of nationality: JAPAN
         Country of residence: JAPAN

15   3.   Agent
         Name: Patent Attorney (9975), AOKI Atsushi
         Address: A. AOKI, ISHIDA & ASSOCIATES
                  Toranomon 37 Mori Bldg., 5-1, Toranomon
                  3-chome, Minato-ku, Tokyo 105-8423 Japan
20   Telephone 03-5470-1900

       4.   Item to be Amended: Claims and Description
       5.   Content of Amendment
       (1) In the description, lines 15 to 19 on page 4, "Si is
25 in a specific range considerably narrower than usual, by
    making the contents of Ti, Nb, Mo, and B specific ranges
    and making the total amount of addition within a suitable
    range" is amended to "Si is limited to a specific range,
    further the contents of Ti, Nb, Mo, and B are made
30 specific ranges and the total amount of addition is made
    within a suitable range".
    (2) In the description, line 15 on page 5, "0.64 to less
    than 0.92" is amended to "0.64 to less than 0.90".
    (3) In the description, line 16 on page 5, "TSxEl" is
35 amended to "TSxEl$^{1/2}$".
    (4) In the description, lines 30 on page 5, "0.68 to
    less than 0.92" is amended to "0.72 to less than 0.90".

LSV 32024840445

- 2 -

(5)   In the description, lines 17 to 18 on page 13, "0.68 to less than 0.92" is amended to "0.72 to less than 0.90".

(6)   In the description, line 19 on page 13, "less than 0.68" is amended to "less than 0.72".

(7)   In the description, line 23 on page 13, "0.92 or more" is amended to "0.90 or more".

(8)   In the description, line 27 on page 13, "less than 0.92" is amended to "less than 0.90".

(9)   In the description, lines 31 to 32 on page 13, "0.72 to 0.90, still more preferably 0.76 to 0.88" is amended to "0.76 to 0.88".

(10) In the description, line 2 on page 19, "TSxEl" is amended to "TSxEL$^{1/2}$".

(11) In the description, line 2 on page 19, "TSxEl≥" is amended to "TSxEL$^{1/2}$≥".

(12) In the claims, "0.64 to less than 0.92" of claim 1 (page 49) is amended to "0.64 to less than 0.90".

(13) In the claims, "TSxEl" of claim 1 (page 49) is amended to "TSxEL$^{1/2}$".

(14) In the claims, "0.68 to less than 0.92" of claim 3 (page 49) is amended to "0.72 to less than 0.90".

6.   Inventory of Attached Documents

(1)	New page of page 4,	1 sheet
(2)	New page of page 5,	1 sheet
(3)	New page of page 13,	1 sheet
(4)	New page of page 19,	1 sheet
(5)	New page of page 49 (claims 1 to 3),	1 sheet

- 4 -

performance due to the effect on secondary materials,
that is, it was difficult to satisfy all of the needs.

   To deal with this, upper and lower limits have been
set for the amounts of addition of these elements, but
5   even this cannot be said to be sufficient.

   In particular, up to now there has not been any
range of limitation of components satisfying all at once
the high yield ratio and ductility and weldability
required for recent automobile frame parts. This has
10   become one of the challenges to be solved by R&D
personnel.

   Therefore, the inventors engaged in various studies
to provide the above steel sheet and as a result took
note of the relationship between the range of Si and
15   specific elements and discovered that when Si is limited
to a specific range, further the contents of Ti, Nb, Mo,
and B are made specific ranges and the total amount of
addition is made within a suitable range by a relation
using specific coefficients to balance the different
20   elements with each other, a high yield ratio and
ductility can both be achieved and weldability can also
be provided and further discovered that by producing the
sheet under suitable hot-rolling and annealing
conditions, these performances can be improved more.

25   Regarding the yield ratio, the fact that a higher
ratio is advantageous from the viewpoint of the collision
absorption energy was explained above, but if too high,
the shape freezability at the time of press formation
becomes inferior, so it is important that the yield ratio
30   not be 0.92 or more.

   The present invention was completed based on the
above discovery and has as its gist the following:

   (1) High yield ratio high-strength thin steel sheet
superior in weldability and ductility, characterized by:
35   being comprised of steel containing, by mass%,

   C: over 0.030 to less than 0.10%,

- 5 -

       Si: 0.30 to 0.80%,

       Mn: 1.7 to 3.2%,

       P: 0.001 to 0.02%,

       S: 0.0001 to 0.006%,

5   Al: 0.060% or less,

       N: 0.0001 to 0.0070%,

containing further

       Ti: 0.01 to 0.055%,

       Nb: 0.012 to 0.055%,

10   Mo: 0.07 to 0.55%,

       B: 0.0005 to 0.0040%, and

simultaneously statisfying

       $1.1 \leq 14 \times Ti(\%) + 20 \times Nb(\%) + 3 \times Mo(\%) + 300 \times B(\%) \leq 3.7$,

the balance comprised of iron and unavoidable impurities,

15 and having a yield ratio of 0.64 to less than 0.90, a

$TS \times El^{1/2}$ of 3320 or more, an $YR \times TS \times El^{1/2}$ of 2320 or more,

and a maximum tensile strength (TS) of 780 MPa or more.

     (2) High yield ratio high-strength thin steel sheet

superior in weldability and ductility as set forth in

20 (1), characterized by further containing, by mass%, one

or two of

       Cr: 0.01 to 1.5%

       Ni: 0.01 to 2.0%,

       Cu: 0.001 to 2.0%,

25   Co: 0.01 to 1%,

       W: 0.01 to 0.3%.

     (3) High yield ratio high-strength hot-rolled steel

sheet superior in weldability and ductility as set forth

in (1) or (2), characterized in that said yield ratio is

30 0.72 to less than 0.90 and in that an X-ray intensity

ratio of a {110} plane parallel to the sheet surface at

1/8 the thickness of the steel sheet is 1.0 or more.

     (4) High yield ratio high-strength cold-rolled

steel sheet superior in weldability and ductility as set

35 forth in (1) or (2), characterized in that said yield

ratio is 0.64 to less than 0.90 and in that an X-ray

intensity ratio of a {110} plane parallel to the sheet

- 13 -

ductility and weldability can be secured with a good
balance is not clear, but it is believed that the
strength of the ferrite and the hardness of the bainite
are suitably balanced and the contradictory
5   characteristics of a high yield ratio and good ductility
can be both achieved.

Further, for the weld zone as well, it is believed
that the distribution of the hardness of the nuggets and
HAZ (heat affected zone) becomes smooth. The range of the
10   above relationship was made 1.1 to 3.7. If less than 1.1,
a high yield ratio is difficult to obtain and the weld
strength also falls.

Further, if over 3.7, the ductility deteriorates, so
3.7 is made the upper limit. A more preferable range is
15       $1.5 \leq 14 \times Ti(\%) + 20 \times Nb(\%) + 3 \times Mo(\%) + 300 \times B(\%) \leq 2.8$.

The yield ratio of the steel sheet obtained in the
present invention is, with a hot-rolled steel sheet, 0.72
to less than 0.90 and, further, with a cold-rolled steel
sheet, 0.64 to less than 0.90. If less than 0.72 in the
20   case of hot-rolled steel sheet and if less than 0.64 in
the case of cold-rolled steel sheet, a sufficient
collision safety cannot be secured in some cases.

On the other hand, if 0.90 or more in the case of
hot-rolled steel sheet and if 0.90 or more in the case of
25   cold-rolled steel sheet, the shape freezability at the
time of press formation deteriorates, so the upper limit
is made less than 0.90 in the case of hot-rolled steel
sheet and less than 0.90 in the case of cold-rolled steel
sheet.
30   In the case of hot-rolled steel sheet, the ratio is
more preferably 0.76 to 0.88. Further, in the case of
cold-rolled steel sheet, the ratio is more preferably
0.68 to 0.88, still more preferably 0.74 to 0.86. Note
that the yield ratio is evaluated by a JIS No. 5 tensile
35   test piece having a direction perpendicular to the
rolling direction as a tensile direction.

-' 19 -

area rate of the different phases.

TSxEl$^{1/2}$ is preferably TSxEl$^{1/2}$≥3320 for obtaining a superior ductility assuming a high-strength steel sheet having a tensile strength of 780 MPa or more. If less

5   than 3320, the ductility cannot be secured in many cases and the balance of strength and ductility is lost.

Further, YRxTSxEl$^{1/2}$ is preferably YRxTSxEl$^{1/2}$≥2320 or more in order to obtain a high yield ratio and superior ductility assuming a high-strength steel sheet having a

10   tensile strength of 780 MPa or more. If less than 2320, the yield ratio or ductility cannot be secured in many cases and the balance is poor.

Next, the inventions of the above (9), (10), and (11), that is, the methods of production of the high

15   yield ratio high-strength hot-rolled steel sheet superior in weldability and ductility, high yield ratio high-strength hot-dip galvanized hot-rolled steel sheet, and high yield ratio high-strength hot-dip galvannealed hot-rolled steel sheet will be explained.

20   The steel components may be adjusted by the usual blast furnace-converter method or an electric furnace etc.

The casting method is also not particularly limited. The usual continuous casting method, ingot method, or

25   thin slab casting may be used to produce a cast slab.

The cast slab may be cooled once, reheated, then hot-rolled or may be directly hot-rolled without cooling.

Once the temperature falls below 1160°C, the sheet is heated to 1160°C or more. If the heating temperature is

30   less than 1160°C, due to segregation and other effects, the product deteriorates in bendability and hole-expandability, so 1160°C is made the lower limit. Preferably, the temperature is made 1200°C or more, more preferably 1230°C or more.

35   The final finishing temperature of the hot-rolling is made the Ar$_3$ transformation temperature or more. If

-· 49 -

CLAIMS

1.   High yield ratio high-strength·thin steel sheet superior in weldability and ductility, characterized by;

being comprised of steel containing, by mass%,

5   C: over 0.030 to less than 0.10%,

Si: 0.30 to 0.80%,

Mn: 1.7 to 3.2%,

P: 0.001 to 0.02%,

S: 0.0001 to 0.006%,

10   Al: 0.060% or less,

N: 0.0001 to 0.0070%,

containing further

Ti: 0.01 to 0.055%,

Nb: 0.012 to 0.055%,

15   Mo: 0.07 to 0.55%,

B: 0.0005 to 0.0040%, and

simultaneously statisfying

$1.1 \leq 14 \times Ti(\%) + 20 \times Nb(\%) + 3 \times Mo(\%) + 300 \times B(\%) \leq 3.7$,

the balance comprised of iron and unavoidable impurities,

20   and

having a yield ratio of 0.64 to less than 0.90, a $TSxEl^{1/2}$ of 3320 or more, an $YRxTSxEl^{1/2}$ of 2320 or more, and a maximum tensile strength (TS) of 780 MPa or more.

2.   High yield ratio high-strength thin steel sheet

25   superior in weldability and ductility as set forth in claim 1, characterized by further containing, by mass%, one or two of

Cr: 0.01 to 1.5%

Ni: 0.01 to 2.0%,

30   Cu: 0.001 to 2.0%,

Co: 0.01 to 1%,

W: 0.01 to 0.3%.

3.   High yield ratio high-strength hot-rolled steel sheet superior in weldability and ductility as set forth

35   in claim 1 or 2, characterized in that said yield ratio is 0.72 to less than 0.90 and in that an X-ray intensity ratio of a (110) plane parallel to the sheet surface at